

Soudafoam Gap Filler Hand Held

Revision: 30/08/2016

Page 1 from 2

Technical data

Basis	Polyurethane
Consistency	Stable foam, thixotropic
Curing system	Moisture curing
Skin Formation (FEICA TM 1014)	8 min
Cutting Time (FEICA TM 1005)	55 min
Density	Ca. 27 kg/m ³
Insulation factor (DIN52612)	37 mW/m.K
Curing time	90 min for a 30 mm bead
Box Yield (FEICA TM 1003)	500 ml yields ca. 20 l of foam 750 ml yields ca. 27 l of foam
Shrinkage (FEICA TM 1004)	< 2 %
Post-expansion (FEICA TM 1004)	< 2 %
Cellular Structure	Ca. 70 % closed cells
Fire rating (DIN4102)	B3
Compressive strength (FEICA TM 1011)	Ca. 2,0 N/cm ²
Shear strength (FEICA TM 1012)	Ca. 5,0 N/cm ²
Water absorption	1 % volume
Temperature resistance	-40 °C till +90 °C (cured)

Soudal NV uses test methods approved by FEICA designed to deliver transparent and reproducible test results, ensuring customers have an accurate representation of product performance. FEICA OCF test methods are available at: <http://www.feica.com/our-industry/pu-foam-technology-ocf>. FEICA is a multinational association representing the European adhesive and sealant industry, including one-component foam manufacturers. Further information at: www.feica.eu

Product description

Soudafoam Gap Filler Hand Held is a one-component, self-expanding, ready to use PU-foam, which contains propellants who are not harmful for the ozonlayer.

- All foam applications in static and not static joints.

Packaging

Colour: champagne

Packaging: 500 ml and 750 ml aerosol (net)

Properties

- Excellent stability (no shrinkage or post-expansion)
- High filling capacity
- Good adhesion on all surfaces (except PE, PP and PTFE).
- High insulation value, thermal and acoustic
- Very good bonding properties.

Shelf life

12 months unopened and stored in dry and cool conditions, Upright storage is recommended

Applications

- Filling of cavities.
- Sealing of all openings in roof constructions.
- Apply of an acoustic baffle
- Improving thermal isolation in cooling systems.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

Soudafoam Gap Filler Hand Held

Revision: 30/08/2016

Page 2 from 2

Application method

Shake the aerosol can for at least 20 seconds.
Put the adapter on the valve. Moisten surfaces with a water sprayer prior to application. For non-conventional substrates a preliminary adhesion test is recommended. Remove pressure from the applicator to stop. Fill holes and cavities for 1/3, as the foam will expand. Repeat shaking regularly during application. If you have to work in layers repeat moistening after each layer. Fresh foam can be removed using Soudal Gun & Foamcleaner or acetone. Cured foam can only be removed mechanically or with Soudal PU-Remover.

Can temperature: +5 °C - 30 °C

Ambient temperature: +5 °C - 30 °C.

Surface temperature: +5 °C - 35 °C

Health- and Safety Recommendations

Take the usual labour hygiene into account.
Always wear gloves and goggles. Remove cured foam mechanically. Never burn away.
Consult label and material safety data sheet for more information.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.