



Silirub 2

Revision: 24/12/2014 Page 1 from 2

Technical data

1 common data	
Basis	Polysiloxane
Consistancy	Stable paste
Curing system	Moisture curing
Skin formation* (20°C / 65% R.H.)	Ca. 5 min
Curing speed * (20°C / 65% R.H.)	Ca. 2 mm/24h
Hardness	25 ± 5 Shore A
Density	Ca. 1,03 g/ml (transp, brilliant white)
	Ca. 1,25 g/ml (colours)
Elastic recovery (ISO 7389)	> 80 %
Maximum allowed distortion	25 %
Temperature resistance	-60 °C → 180 °C
Max. tension (DIN 53504)	1,60 N/mm²
Elasticity modulus 100% (DIN 53504)	0,38 N/mm²
Elongation at break (DIN 53504)	800 %
Application temperature	$5 ^{\circ}\text{C} \rightarrow 35 ^{\circ}\text{C}$

^(*) these values may vary depending on environmental factors such as temperature, moisture, and type of substrates.

Product description

Silirub 2 is a high-quality, neutral, elastic onecomponent joint sealant based on fast skinning silicones.

Properties

- Very easy to apply
- Colourfast and UV resistant
- Permanent elastic after curing
- Very good adhesion on many materials
- Low modulus
- Corrosion free

Applications

- All usual building joints with high movement.
- All glazing and joint works.
- Expansion joints between many different construction materials.
- Sealing between PVC, treated wooden and metal profiles and glass.

Packaging

Colour: transparent, white, grey, alu grey, black, brown, teak, bronze, beige, light brown, oak, stone, dark brown, natural stone, terra cotta, buff, brilliant white, toffee, basalt grey, dark gey

Packaging: 310 ml cartridge, 300 ml sausage, 600 ml sausage

Shelf life

18 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.

Substrates

Substrates: all usual building substrates Nature: clean, dry, free of dust and grease. Surface preparation: Porous surfaces in water loaded applications should be primed with Primer 150. No primer needed for non-porous substrates.

There is no adhesion on PE, PP, PTFE (Teflon®) and bituminous substrates. We recommend a preliminary compatibility test.

Remark: This technical data sheet replaces al previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions beyond our control, no liability under this publication are accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

 Soudal NV
 Everdongenlaan 18 - 20
 BE-2300 Turnhout

 Tel: +32 (0)14-42.42.31
 Fax: +32 (0)14-42.65.14
 www.soudal.com





Silirub 2

Revision: 24/12/2014 Page 2 from 2

Compatibility with glass

Tests carried out in our laboratories show that Silirub 2 is compatible with most edge seals of insulating double glazing and conventional PVB films. External testing at TÜV Rheinland have shown no visual defects or no other inconsistencies that were found between the secondary seal or PVB film and Silirub 2 after exposure to high temperature and humidity (Report No. 12490R-a-89202273). Due to the large number of edge sealing systems on the market, it is impossible to test the compatibility of all combinations with glazing sealants.

Joint dimensions

Min. width for joints: 5 mm Max. width for joints: 30 mm Min. depth for joints: 5 mm

Recommendation sealing jobs: joint width = 2

x joint depth.

Application method

Application method: With manual- or pneumatic caulking gun.
Cleaning: Clean with white spirit or Surface Cleaner immediately after use.
Finishing: With a soapy solution or Soudal

Finishing Solution before skinning.

Repair: With the same material

Health- and Safety Recommendations

Take the usual labour hygiene into account. Consult the packaging label for more information.

Remarks

- Do not use on natural stones like marble, granite,...(staining). Use Soudal Silirub MA for this application.
- A total absence of UV can cause a color change of the sealant.

Standards

- Belgium: ATG 1808 (NIT 107) Conform to ISO 11600 F+G 25LM
- Report IANESCO 3812-food label for applications in food surroundings.

 Report IANESCO 551, conformity to FDA CFR 21 §177.2600 (e)

Gemany: DIN 18540 Teil 2 – DIN 18545
 Teil 2 Dichtstoffgruppe E

Environmental clauses

Leed regulation:

Silirub 2 conforms to the requirements of LEED. Low –Emitting Materials: Adhesives and Sealants. SCAQMD rule 1168. Complies with USGBC LEED® 2009 Credit 4.1: Low-Emitting Materials – Adhesives & Sealants concerning the VOC-content.

Remark: This technical data sheet replaces al previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions beyond our control, no liability under this publication are accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

 Soudal NV
 Everdongenlaan 18 - 20
 BE-2300 Turnhout

 Tel: +32 (0)14-42.42.31
 Fax: +32 (0)14-42.65.14
 www.soudal.com